

SABA Sealcoat CR

conductive and high chemical resistant coating for horizontal surfaces

Description

SABA Sealcoat CR is a 2-component, self-levelling, crack-sealing, elastic polysulphide-based coating for coating horizontal surfaces. Due to its high chemical resistance and conductive character, this product is suitable for a variety of applications in the chemical industry.

Field of application

Civil & environmental engineering, including the chemical industry. SABA Sealcoat CR is especially suitable for coating stone, tile and metal horizontal surfaces that require protection and for coating liner material in calamity rooms, tanks and silos, reservoirs and gutters.

Advantages

- self-levelling
- durable and weather-resistant
- · can be used on concrete constructions for emergency storage, prefab constructions, for example
- resistant to solvents and chemicals, resistant to motor fuels such as petrol, diesel oil, hydraulic oil and LPG (for more information please contact SABA)
- contains no solvents
- conforms to DIBt, Allgemeine bauaufsichtliche Zulassung Z-59.12-201, coating systems for concrete in LAU facilities

Method of use

For more information about the method of use and pre-treatment, see the relevant SABA info sheets and pre-treatment tables at www.saba.nl

Technical data

	Part A	Part B	
Basis	polysulphide	anorganic peroxide	
Viscosity (EN 12092)	self-levelling	approx. 30 Pa.s	
Density (EN 542)	approx. 1,430 kg/m ³	approx. 1,690 kg/m ³	
Solids content	approx. 100%	approx. 100%	
Application time	approx. 1.5 hours		
Curing time (23 °C, 50% RLV)	approx. 24 hours		
Hardness Shore A (EN ISO 868)	approx. 25		
Volume alteration (EN ISO 10563)	approx. 2%		
Working temperature	min. + 5 °C to max. + 35 °C		
Storage temperature	min. + 5 °C to max. + 25 °C		
Temperature resistance	min 40 °C to max. + 120 °C		

Order information

Packaging	set (A and B component)	
Contents	2.5 litres (contains 4 items)	7.5 litres (contains 1 item)
Colour	grey	grey
Article no.	100284 ABG	100284 ABE
Shelf life	18 months (in unopened packaging)	

Other packaging and colours on request. The shelf life may vary for large packaging.

Safety recommendations

For more information about safety, see the relevant SABA safety data sheets.

SABA Dinxperlo BV

Industriestrant 3 NL-7091 DC Dinxperlo PO Box 3 NL-7090 AA Dinxperlo T+31 (0) 315 658999 F+31 (0) 315 653989 E info@saba.nl www.saba.nl

Our recommendations and instructions for use are based on the present status of know-how and technique. Clients and users should evaluate our products by themselves, with regard to utilization and requirements of their own choice. We shall take no responsibility in case our products are not being used subject to our recommendations and/or instructions for use. Furthermore, General Terms and Conditions of SABA Dinxperlo BV, will apply to our recommendations, instructions for use and the delivery of our products.