

Description

SABA Primer H17 is a 2-component epoxy primer for porous substrates.

Field of application

SABA Primer H17 is suitable for the pre-treatment of porous substrates prior to the use of SABA polysulphide sealants/coatings.

Advantages

- very good resistance to moisture, solvents, acids and alkalis
- complies with EN 14188-4

Method of use

For more information about the method of use, see the relevant SABA info sheets at www.saba.nl

Closing the pack as quickly as possible after use has a positive effect upon the application properties and shelf life of the product.

Technical data

	Part A	Part B
Base	epoxide	amine
Viscosity at 23 °C (EN 12092)	watery	watery
Density	approx. 1,010 kg/m ³	approx. 900 kg/m ³
Solid content	approx. 45%	approx. 30%
Flash point	approx.+ 12°C	
Solvents	mixture of aromatics and esters	
Drying time (minimum)	30 minutes	
Open time (maximum)	6 hours	
Application time	approx. 2-3 hours	
Coverage	approx. 150 g/m ²	
Application temperature	minimum + 5°C to maximum + 30°C	
Storage temperature	minimum + 5°C to maximum + 30°C	
Temperature resistance	minimum - 40°C to maximum + 120°C	

Order information

Packaging	set (A + B component)		
Contents	500 ml (contains 6 items)	900 ml (contains 6 items)	4 litres (contains 1 item)
Colour	light yellow		
Article no.	100324 AFL	100324 AFH	100324 ABB
Shelf life	18 months (in unopened packaging)		

Other packaging and colours on request. The shelf life may vary for large packaging.

Safety recommendations

For more information about safety, see the relevant SABA safety data sheet.



SABA Dinxperlo BV

Industriestraat 3 NL-7091 DC Dinxperlo PO Box 3 NL-7090 AA Dinxperlo T+31 (0) 315 65 89 99 F+31 (0) 315 65 89 89 E info@saba.nl www.saba.nl



Our recommendations and instructions for use are based on the present status of know-how and technique. Clients and users should evaluate our products by themselves, with regard to utilization and requirements of their own choice. We shall take no responsibility in case our products are not being used subject to our recommendations and/or instructions for use. Furthermore, General Terms and Conditions of SABA Dinxperlo BV, will apply to our recommendations, instructions for use and the delivery of our products.