

Description

Sabadrain is a sealant 1-component, elastic, (air) moisture-curing based on MS-poly for sealing joints around drain gutters.

Field of application

Sabadrain is suitable for sealing joints around stainless steel drain gutters in sanitaire spaces.

Advantages

- Permanently elastic
- no blistering
- odorless in processing
- free from solvents, silicones and isocyanates
- high end strength
- able to resist temperature shocks
- easy to operate
- CE mark on the basis of EN 15651-1, Type XS2

Method of use

For instructions for use, repaintability and pre-treatment, see the relevant info sheets at www.saba.nl

Technical data

Basis	MS polymer, humidity-curing
Density (EN 542)	approx. 1.390 kg/m ³
Solids content	approx. 100%
Open time (23 °C, 50% RLV)	approx. 10 minutes
Tack free (23 °C, 50% RLV)	after approx. 4 hours
Cure rate (23 °C, 50% RLV)	approx. 4 mm/24 hrs
Hardness Shore A (EN ISO 868)	approx. 55
Loss of volume (EN ISO 10563)	< 5%
Modulus at 100% elongation (ISO 37/DIN 53504)	approx. 1.5 N/mm ²
Tensile strength (Fmax) (ISO 37/DIN 53504)	approx. 3.0 N/mm ²
Elongation at break (ISO 37/DIN 53504)	approx. 350%
Shear strength (ISO 4587)	approx. 1.8 N/mm ²
Working temperature	min. +5 °C to max. +35 °C
Storage temperature	min. +5 °C to max. +25 °C
Temperature resistance	min. -40 °C to max. +100 °C

Order information

Packaging	sausage
Contents	400 ml (contains 12 pcs)
Colour	grey
Article no.	101032 AAM
Shelf life	15 months (in unopened packaging)

Other packaging and colours on request. The shelf life may vary for large packaging.

Safety recommendations

For more information about safety, see the relevant SABA Safety Data Sheet.



SABA Dinxperlo BV
Industriestraat 3 NL-7091 DC Dinxperlo PO Box 3 NL-7090 AA Dinxperlo T+31 (0) 315 658999 F+31 (0) 315 653989 E info@saba.nl www.saba.nl

Our recommendations and instructions for use are based on the present status of know-how and technique. Clients and users should evaluate our products by themselves, with regard to utilization and requirements of their own choice. We shall take no responsibility in case our products are not being used subject to our recommendations and/or instructions for use. Furthermore, General Terms and Conditions of SABA Dinxperlo BV, will apply to our recommendations, instructions for use and the delivery of our products.