



SABA Primer 9911

primer for bituminous substrates

Description

SABA Primer 9911 is a 2-component epoxy primer for bituminous substrates.

Field of application

SABA Primer 9911 is suitable for the pre-treatment of bituminous substrates such as asphalt concrete.

Advantages

- also suitable for porous substrates

Method of use

For more information about the method of use and pre-treatment, see the relevant SABA info sheets and pre-treatment tables at www.saba.nl

Closing the pack as quickly as possible after use has a positive effect upon the application properties and shelf life of the product.

Technical data

	Part A	Part B
Base	epoxide	amine
Viscosity at 23 °C (EN 12092)	watery	watery
Density (EN ISO 2811-2)	approx. 950 kg/m ³	approx. 1125 kg/m ³
Solid content	approx. 37%	approx. 100%
Solvents	ketones	none
Flash point	approx.+ 12°C	
Drying time (minimum)	30 minutes	
Open time (maximum)	6 hours	
Application time	2 to 3 hours	
Coverage	approx. 100 g/m ²	
Application temperature	minimum + 5°C to maximum + 30°C	
Storage temperature	minimum + 5°C to maximum + 30°C	
Temperature resistance	minimum - 40°C to maximum + 120°C	

Order information

Packaging	set (A + B component)
Contents	0.5 litres (contains 6 items)
Colour	light yellow
Article no.	100485 AAS
Shelf life	18 months (in unopened packaging)

Other packaging on request. The shelf life may vary for large packaging.

Safety recommendations

For more information about safety, see the relevant SABA safety data sheet.



SABA Dinxperlo BV

Industriestraat 3 NL-7091 DC Dinxperlo PO Box 3 NL-7090 AA Dinxperlo T+31 (0) 315 65 89 99 F+31 (0) 315 65 89 89 E info@saba.nl www.saba.nl

Our recommendations and instructions for use are based on the present status of know-how and technique. Clients and users should evaluate our products by themselves, with regard to utilization and requirements of their own choice. We shall take no responsibility in case our products are not being used subject to our recommendations and/or instructions for use. Furthermore, General Terms and Conditions of SABA Dinxperlo BV, will apply to our recommendations, instructions for use and the delivery of our products.